

CORE & TECHNICAL

Products

MDF ST CARB2/TSCA

Medium density fiberboard for general use in dry conditions

DESCRIPTION

Sonae Arauco MDF ST CARB2/TSCA is a medium density fibreboard for interior use, suitable for furniture production and easy to mill. MDF ST CARB2/TSCA has low formaldehyde emission, is certified according to the rules of the official California Air Resources Board (CARB) and compliant with limit of ChemVerbotsV (E05).

Regarding reaction to fire and according to EN 13986, MDF ST CARB2/TSCA, with a thickness ≥ 9 mm and a minimum density of 600 Kg/m^3 , is classified as D-s2, d0 (Euroclasses definition by EN 13501-1).

In addition to technical performance MDF ST CARB2/TSCA panels are sustainable and environmental friendly products.

Please check offer & service brochure for information on sizes and thicknesses available.

APPLICATIONS

MDF ST CARB2/TSCA is a versatile material and can be used as the basic product for designers and manufacturers. Due to the wood fibers used in its production, the product presents a homogeneous surface, giving it a good dimensional stability and ability to be easily machined.

The density of the surface also gives the possibility of using a wide range of finishing techniques as lacquering, coating, veneering, foil wrapping and covering.

PROPERTIES



VERSATILITY



EASY TO MILL



EPA TSCA TITLE VI & CARB 2 CERTIFIED



COMPLIANT WITH CHEMVERBOTS V

APPLICATIONS



FURNITURE



KITCHENS



OFFICES & EDUCATION



RESTAURANTS & HOTELS



HEALTH & WELLNESS



RETAIL & EXHIBITIONS



DOORS



PANELING



CONSTRUCTIONS

RECOMMENDATIONS

Boards must be stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

ALSO AVAILABLE



FIRE RETARDANT



MOISTURE RESISTANT



NON ADDED FORMALDEHYDE

www.sonaearauco.com

TDS.03.06.SAD.R01

MDF ST CARB2/TSCA

Medium density fiberboard for general use in dry conditions

GENERAL CHARACTERISTICS

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)					
			6	>6 - 9	>9 - 12	>12 - 19	>19 - 30	>30 - 40
Tolerance on thickness	EN 324-1	mm	± 0,2	± 0,2	± 0,2	± 0,2	± 0,3	± 0,3
Tolerance on length and width	EN 324-1	mm/m	± 2	± 2	± 2	± 2	± 2	± 2
Edge straightness tolerance	EN 324-2	mm/m	≤ 1,5	≤ 1,5	≤ 1,5	≤ 1,5	≤ 1,5	≤ 1,5
Squareness tolerance	EN 324-2	mm/m	≤ 2	≤ 2	≤ 2	≤ 2	≤ 2	≤ 2
Tolerance on mean density	EN 323	%	± 7	± 7	± 7	± 7	± 7	± 7
Moisture content	EN 322	%	4 - 11	4 - 11	4 - 11	4 - 11	4 - 11	4 - 11

TECHNICAL INFORMATION

PROPERTY	TEST	UNIT	THICKNESS RANGE (mm)					
			6	>6 - 9	>9 - 12	>12 - 19	>19 - 30	>30 - 40
Density *	EN 323	Kg/m ³	760	760	750	735	735	730
Bending strength	EN 310	N/mm ²	≥ 26	≥ 26	≥ 25	≥ 25	≥ 24	≥ 22
Modulus of elasticity	EN 310	N/mm ²	≥ 3000	≥ 3000	≥ 2800	≥ 2800	≥ 2600	≥ 2500
Internal bond	EN 319	N/mm ²	≥ 0,72	≥ 0,72	≥ 0,65	≥ 0,65	≥ 0,60	≥ 0,55
Thickness swelling 24 hours	EN 317	%	≤ 30	≤ 17	≤ 15	≤ 12	≤ 10	≤ 8
Formaldehyde emission class	CARB Phase 2 / EPA TSCA **							

* Value to be used only as a reference

**compliant with limit of ChemVerbotsV (E05)

MDF ST CARB2/TSCA boards meet the specification of EN 622, type MDF, and is CE marked. For more information regarding the technical properties, please check the product Declaration of Performance (DoP).

CERTIFICATIONS

Please pay attention to certified products:



The mark of
responsible forestry
FSC® C009049



Promoting
Sustainable Forest
Management
PEFC™
PEFC04-32-0787 www.pefc.org



FSC® and PEFC™ -certified products are available on request and availability.

www.sonaearauco.com

TDS.03.06.SAD.R01

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and / or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.